



Connecticut Location
 3 Mattoon Road
 Waterbury, CT 06708
 Phone: 203.591.1770
 Fax: 203-591.1804
866.558.0111

Ohio Location
 6115 Centre Park Drive
 West Chester, OH 45069
 Phone: 513.779.6166
 Fax: 513.777.8959
800.255.1104

Minnesota Location
 6251 McKinley Street NW
 Ramsey, MN 55303
 Phone: 763.421.8400
 Fax: 763.421.1304
800.747.4815

Material Specifications

	Density (g/cm3)	Grain Size (microns)	Flex Strength (psi)	Hardness (shore)
CP/EMS Grades:				
CP - 55/EMS -1000	1.70	20	7,000	50
CP - 60/EMS -1500	1.75	15	8,530	53
CP - 65/EMS- 3800	1.75	13	9,240	55
CP - 70/EMS- 5000	1.80	10	11,630	62
EMS-5000C	2.75	10	7,600	65
CP3000/EMS -7000	1.80	5	13,000	70
EDX-7	1.82	5	13,500	68
CP-3000C/EMS-7000C	2.86	10	13,000	60
Poco Grades:				
EDM - 200	1.82	10	9,000	64
EDM - 1	1.66	5	7,500	70
EDM - 3	1.81	5	13,500	76
EDM - 4	1.80	<4	15,800	76
EDMC - 3	3.05	5	16,500	67
EDM AF-5	1.80	1	17,000	87
EDMC - 200	2.86	10	13,000	60